

January 27, 2004

Mr. Todd Beehler  
Contego International, Inc.  
P.O. Box 49  
Rochester, NY 46975-0049

Dear Mr. Beehler,

The two coated samples you submitted to Touchstone Research Laboratory for Adhesion testing were evaluated according to the methods prescribed in ASTM D3359, "Standard Methods for Measuring Adhesion by Tape Test". Both samples were tested according to method "A", X-cut tape test and Method "B", cross-cut tape test. The results are provided on the following page. Both methods indicate 0% paint loss by peeling or removal.

If there are any questions regarding these results please contact me at your convenience.

Best regards,

  
H.L. Stauver

**Standard Test Method for Measuring Adhesion by Tape Test  
ASTM D3359**

**Classification Rating**

	<u>Method A</u>	<u>Method B</u>
Aluminum	5A	5B
Steel	5A	5B

5A = No peeling or removal

5B = No peeling or removal