



Akrediteeritud
L020

TÜV EESTI OÜ

Masina 11, 10144 Tallinn, Estonia
tel +372 60 75 918 ; fax +372 63 79 601
e-mail: info@tuev-nord.ee

Testing Laboratory:

Vana-Narva mnt. 24B, Maardu, Estonia
tel +372 63 79 306; faks +372 63 79 601
e-mail: test@tuev-nord.ee



Page 1 of 3

CLASSIFICATION OF REACTION TO FIRE in accordance with EVS-EN 13501-1:2007

SPONSOR: Purfin Oy

ADDRESS : Kiperhaantie 8, FI-21250 Masku, Finland

MANUFACTURER: Purfin Oy

ADDRESS : Kiperhaantie 8, FI-21250 Masku, Finland

PREPARED BY: TÜV EESTI OÜ

NOTIFIED BODY No: 1526

PRODUCT NAME : PU-insulation Ekospray 40E with Sika Unitherm Wood P coating

CLASSIFICATION REPORT : TEK- 76/12en

ISSUE NUMBER :

DATE OF ISSUE :



This classification report consists of four (3) pages.



Accreditation
L020

TÜV EESTI OÜ

Vana-Narva mnt. 24B, Maardu, Estonia
tel +372 60 75 918 ; fax +372 63 79 601
e-mail: info@tuev-nord.ee

Testing Laboratory:
tel +372 63 79 306; faks +372 63 79 601
e-mail: test@tuev-nord.ee



Classification report no. TEK-76/12 en

Page 2 of 3

1. Introduction.

This classification report in accordance with the procedures given in EVS-EN 13501-1:2007 defines the reaction to fire classification assigned to the polyurethane foam layer by Purfin Oy covered with fire retardant paint by Sika Österreich GmbH.

2. Classified product.

2.1 General

Product is defined as a PU-insulation Ekospray 40E with fire retardant paint coating.

2.2 Description

The product was sprayed in layers 15-25 mm to veneer board. Overall layer varied from 50 to 65 mm. The excessive material was cut off from unexposed side of the specimens to achieve thickness 50 mm.

3. Test reports / extended application reports and test results in support of the classification.

3.1. Test reports and extended application reports

Test Laboratory	Name of sponsor	Test report and date	Test method
TÜV Eesti OÜ	Purfin Oy	No. 007-12TM of 31.05.2012	EN 13823:2010
TÜV Eesti OÜ	Purfin Oy	No. 060-11TM of 21.09.2011	EN ISO 11925-2:2010 surface exposure
TÜV Eesti OÜ	Purfin Oy	No. 070-11TM of 01.11.2011	EN ISO 11925-2:2010 edge exposure

3.2. Test results

Test method	Parameter	No. tests	Results	
			Continuous parameter	Compliance
EN 13823:2010	Figra 0,2 MJ (W/s)	5	303	Compliant
	Figra 0,4 MJ (W/s)	5	114	
	THR 600 s (MJ)	5	3,9	
	LFS to edge	5	Did not reach	
	SMOGRA (cm ² /s ²)	5	133,4	
	TSP 600 (m2)	5	199,8	
	Burning particles/drops	5	No drops	
EN ISO 11925-2:2010	Flame spread in excess of 150 mm vertically (applied to edge and surface)	12	Did not reach	Compliant





Accreditation
L020

TÜV EESTI OÜ

Vana-Narva mnt. 24B, Maardu, Estonia
tel +372 60 75 918 ; fax +372 63 79 601
e-mail: info@tuev-nord.ee

Testing Laboratory:
tel +372 63 79 306; faks +372 63 79 601
e-mail: test@tuev-nord.ee



Classification report no. TEK-76/12 en

Page 3 of 3

4. Classification and field of application

4.1 Reference on classification.

This classification has been carried out in accordance with EVS-EN 13501-1:2007/A1:2009

4.2 Classification.

PU- insulation layer Ekospray 40E with fire retardant paint layer is classified to:

Fire behaviour		Smoke production			Flaming droplets	
C	-	s	2	-	d	0

Reaction to fire classification: C-s2,d0

4.3 Field of direct application.

This classification is valid for the following end use applications:

Ekospray 40E PU-insulation layer can be applied to vertical and horizontal combustible and noncombustible surfaces. Polyurethane layer thickness 0-65 mm. Fire retardant paint must be applied with pumpspray in one layer of 560 (g/m²) ±5%.

5. Limitations

This classification report does not represent type approval or certification of the product.

On behalf and by authority of TÜV Eesti OÜ.

Prepared and
approved by

Fred Haas

Head of the laboratory

