

Approved Primers

Primer Requirements:

Prior to apply Contego intumescent coatings **ALL** ferrous and nonferrous metals require primer. If applying Contego intumescent coatings to galvanized metals or aluminum substrates contact Contego International for specific references. All primers must be applied in accordance with the primer manufacturer's written instructions. All primers must be fully cured prior to the application of the Contego intumescent coatings according to manufactures specifications. Failure to comply with the primer manufacturers instruction could void Contego intumescent 2-year warranty.

Special Precautions:

Semi-gloss and gloss sheen primers are not recommended for best adhesion results. Zinc-rich primers are **NOT** approved for use with direct application of Contego intumescent coatings. An additional primer barrier between Contego intumescent coatings and zinc-rich primers are required.

*Please contact the Contego International Technical Services Department at 800-434-6444 or info@contegointernational.com for further assistance or for the use of primers other than those listed.

Introducing Contego RUSTEX 710

Contego RUSTEX 710 Metal Primer HS Low VOC a high performance, universal anti-corrosive primer with excellent adhesion, hardness, durability, and corrosion resistance. The corrosion resistance will surpass in excess of 1000 hours of cyclic corrosion testing using ASTM D 5894 Salt Fog/UV Exposure testing methods.



The High solids content of this coating permits extremely economical use at low film builds, while at the same time enabling higher film builds to achieve coverage over aggressive surface profiles. Formulated for fast dry times with exceptional low temperature curing even during winter conditions.

This primer meets the requirements of AISC 1-73A and MPI 76. and is VOC compliant for non-shop use.

Product Code: 71044 Category: Undercoats and Primers Chemistry: Phenolic Alkyd,

Manufacturer	Product Description
American Coatings	AK Series Shop Coat Primer (AK3333 Gray Primer - Alkyd Resin Primer)
American Coatings	AK11509 Red Oxide HS VOC 2.8
American Coatings	American Coatings AK12946 Gray Iron Oxide
American Coatings	American Coatings AK 16292 2.8 VOC Low HAPs Dark Gray Primer
Ameron International / PPG	Amercoat 5105 Alkyd Primer (oxide red, pearl gray, white)
Behr	Exterior Primer Water Based Primer and Sealer #436
Benjamin Moore & Co.	M14 Shop-Coat Modified Alkyd metal primer
Benjamin Moore & Co.	Super Spec HP Shop Coat Alkyd P-14
Century Industrial Coatings	220-D-252, 220-D-252B
Century Industrial Coatings	RD Red NULO Spray - HAPs Free Primer W/B 220-R-355A
Century Industrial Coatings	120-D-263, 120-D-264, 120-D-331
Century Industrial Coatings	Dark Red Spray Primer 220-R-250/A
Century Industrial Coatings	120-D-224A Gray
Century Industrial Coatings	120-D-326A - 275 Light Gray Spray Primer
Century Industrial Coatings	220-D-358, 220-D-358C
Century Industrial Coatings	120-D-174Q Gray Joist Primer
Century Industrial Coatings	220-R300-103A Fast Dry WB Red Oxide Spray Primer
Century Industrial Coatings	220-D-544B Gray Water-Based Spray Primer
Cloverdale Paint	Industrial Phenolic Modified Alkyd Shop Primer 71019, 71306, 71312
Cloverdale Paints	Universal Phenolic Alkyd Primer 83040 Grey, 83041 Red
Cloverdale Paints	Rustex 710
Cloverdale Paints	839 Eco Logic
Dunn-Edwards	W715 Ultra-Grip Acrylic Multi-Purpose Primer
Farrell Calhoun	1099 Red Tuff Boy
Farrell Calhoun	Tuff Boy QD Low VOC Rust Stop Modified Alkyd primer 5-53 Red & 5-54 Gray
Farrell Calhoun	Tuff Boy Quick Dry 6-30
Kelley Moore Paint	-Gard Metal Primer White 1712-100
Kelley Moore Paint	1760 Sop Coat Alkyd Primer
Kelley Moore Paint	265 KM Professional Water-Oil Hybrid
Miller Paint Co.	Red Oxide Metal Primer Red Oxide #363
Miller Paint Co.	470011 All Purpose Stain Blocking Acrylic Primer
Miller Paint Co.	310210 Acrimetal DTM Low Sheen Acrylic
Pittsburgh Paints	SPEEDHIDE Alkyd Rust Inhibitive Primer 6-208 Red (6-212 White)
PPG	Pure Performance 9-900 Acrylic Primer
PPG	Amerlock 600
PPG	Amerlock 2 VOC
PPG	Multiprime 94-269
PPG	7-852, 7-858 Series Rust Inhibitive Steel Primers Alkyd Resin
PPG	MULTIPRIME Low VOC Quick Dry Universal Alkyd Primer 97-680
PPG	Pitt-Tech Plus 90-1210
PPG	Pitt-Tech Plus Int.Ext. DTM Industrial Primer 90-912 Series
PPG	Multi Primer Fast Dry 2.8 VOC 94-258 Series
PPG	Multiprime 4160
PPG	HPC Industrial Alkyd 4308

PPG	Fast Dry 4190
PPG	Pitt Tech Plus SG 4216H
PPG	Pitt Tech Plus 4020 PF
PPG	Fast Dry 4180
Rodda Paint	P-80 Quick Drying Metal Primer Gray
Rodda Paint	Barrier III High Solids Alkyd Metal Primers
Rodda Paint	Barrier III Rust Inhibitive Metal Primer
Rodda Paint	Barrier III HS Rust Inhibitive Metal Primer
Rodda Paint	6340 Shop Primer 40 Red (LCF) Primer
Rust-Oleum	2068 Quick Dry Red Primer
Rust-Oleum	K7769 Rusty Metal Primer - Alkyd
Sherwin Williams	Pro-Cryl Universal Acrylic Primer B66 Series
Sherwin Williams	E61RC21 Red (E61AC82 gray) Shopcoat Primer
Sherwin Williams	Red Structural Steel Primer B50XXRW4648
Sherwin Williams	Kem Bond HS Universal Metal Primer B50 Series
Sherwin Williams	E61R26 Kem Flash Prime Red Oxide
Sherwin Williams	Industrial Grey Metal Primer SW28
Sherwin Williams	Alkyd QD Primer B50A50 / B50R51
Sherwin Williams	Ironox primer #29 Red
Sherwin Williams	DTM Acrylic Primer/Finish (B66W1)
Sherwin Williams	Kem Bond HS Universal Metal Primer B50 Series
Sherwin Williams	Macropoxy 646 Fast Cure Epoxy (Part A -B58-600, Part B - B58V600)
Sherwin Williams	B74AT83 Utility Shop Coat Fast Dry Alkyd Gray Primer
Sherwin Williams	Ironox Primer 96 Gray
Sherwin Williams	Macropoxy 646-100 (low voc)
Sherwin Williams	B66W310 Pro-Cryl Universal Metal Primer (low voc)
Sumter Coatings	100D2314
Sumter Coatings	100D7714, 100R7713, 100D7720 Inhibitive Shopcoat Primers
Sumter Coatings	100R8813, 100D8814 High Solids Inhibitive Primers
Sumter Coatings	100R9913, 100D9914 Heavy Duty Inhibitive Primers
Sumter Coatings	100D0031,100R0027, 100W0038 Universal Primers
Sumter Coatings	Red Shopcoat Primer (801R2712 / SP 2712)
Sumter Coatings	100R0984, 100D0985 Structural Shopcoat Primers
Sumter Coatings	Sumter Coatings 196D1635
Sumter Coatings	HS Low VOC Inhibitive Primer Gray - 100D8823
Sumter Coatings	Inhibitive Shopcoat Low VOC HS Universal Primer Gray - 100D2230
Sumter Coatings	High Solids - Low VOC Inhibitive Primer (100R8822 Red)
Sumter Coatings	Pretreatment Primer (100G2029 / 100X2030)
Sumter Coatings	100D2314
Sumter Coatings	100D7714, 100R7713, 100D7720 Inhibitive Shopcoat Primers
Sumter Coatings	100R8813, 100D8814 High Solids Inhibitive Primers
Tnemec	FM 88-0559 - modified short oil alkyd
Tnemec	Series FD 88 Azeron - modified alkyd
Tnemec	Series 10-99 Red (10-1009 Gray) modified alkyd
Tnemec	Azeron H.S. Primer Series 88HS, 555 Red, 599 Gray
Tnemec	Uni-Bond DF Series 115 Acrylic Primer

Tnemec	UVX Series 750
Tnemec	2C 118-30GR Mastic WB Acrylic
Tnemec	Tneme-Fascure Series 161 Primer
Tnemec	FM 88-0559 - modified short oil alkyd
Tnemec	Series FD 88 Azerox - modified alkyd
Valspar	High Performance WWA 164-759
Valspar	Duraspar 130 AX Series Primer
Valley Paint Co.	V-006 Universal Metal Primer
Vista Paint	Metal Pro Coating Primer/Finish (4800, 4805, 4810, 4896)
Vista Paint	MP10 Waterborne Red Oxide Shop Primer
Vista Paint	4000 Uniprime Multi-purpose Acrylic
Vista Paint	9600 Protec Metal Prime- Alkyd Emulsion



Prior to apply Contego intumescent coatings **ALL** ferrous and nonferrous metals require primer. If applying Contego intumescent coatings to galvanized metals or aluminum substrates contact Contego International for specific references. All primers must be applied in accordance with the primer manufacturer's written instructions. All primers must be fully cured prior to the application of the Contego intumescent coatings according to manufactures specifications. Failure to comply with the primer manufacturers instruction could void Contego intumescent 2-year warranty.

Semi-gloss and gloss sheen primers are not recommended for best adhesion results. Zinc-rich primers are **NOT** approved for use with direct application of Contego intumescent coatings. An additional primer barrier between Contego intumescent coatings and zinc-rich primers are required.

Contego International assumes no responsibility for the duplication of these results in the field as variations in site conditions, surface preparation, formulation changes and other factors are beyond our control.

*Please contact the Contego International Technical Services Department at 800-434-6444 or info@contegointernational.com for further assistance or for the use of primers other than those listed.

www.contegointernational.com